



Isolator glove

# CSM/Polyurethane/CSM

6/10 mm



### SCOPE

Life sciences (pharmaceutical industry, hospitals), nuclear, industry.

Three-layer inner CSM/intermediate polyurethane/outer CSM glove. Excellent resistance to chemicals and to ionising radiation, ozone and UV. Good mechanical resistance.

■ ■ ■ Economical performance

■ ■ ■ Chemical performance

■ ■ ■ Dexterity performance

■ ■ ■ Mechanical performance

■ ■ ■ Storage performance



IN COMPLIANCE WITH 2016/425 EUROPEAN REGULATION (CATEGORY 3 P.P.E.)



## GENERAL INFORMATION

Chemical composition	Chlorosulfonated Polyethylene / Polyurethane / Chlorosulfonated Polyethylene
Material code	Y/PUR/Y
Colour	White
Packaging	Individually packed in two-toned black and transparent, heat-sealed and easy-opening pouch. Pack of 30 units.
Care instructions	Store in the original packaging between +5°C and +25°C. Expiry date of 3 years in the original packaging. Wash with soapy water, rinse with clear water and then air-dry at a low temperature (<40°C).
Treatment	Non-recyclable. Disposal as simple non-toxic waste if not contaminated by a hazardous substance.
Sterilisation	Can be delivered in a decontaminated version or a decontaminated-sterilised version (sterilisation with Gamma radiation) (pack of 50 units).
Powdering	Standard: lightly powdered gloves.
Disinfectants	Excellent resistance to the following disinfectants: 0.25% Surfanios, 10% Sopropor, 70% Isopropyl alcohol.
Dimensional tolerances	Thickness: 6/10 mm (palm min 4/10, max 8/10). Length: 330 mm. Diameter of the rim: 4 mm (+/-1 mm).

## PHYSICO-CHEMICAL PROPERTIES TEMPERATURE RANGE: -20 TO +120°C

Alcohols	---
Acids, bases	---
Strong oxidants	---
Uv, ozone, free radicals, natural ageing	---
Ketone solvents	---
Chlorinated solvents	---
Aromatic solvents	---
Aliphatic oils and solvents	---
Peracetic acid sterilisation (3%)	---
H2O2 Sterilisation (35%)	---
H2O2 Sterilisation (50%)	---
25-50 kGray gamma radiation	---
Autoclave sterilisation (121°C)	---
Protection from ionising radiation	non

\* --- Not recommended --- Can be used under certain conditions --- Acceptable --- Recommended

## MECHANICAL PROPERTIES

100% Modulus <sup>(1)</sup>	Tear resistance <sup>(1)</sup>	Elongation at tear <sup>(1)</sup>	Perforation (EN 388)
< 3.0 MPa	> 15 MPa	> 300%	> 30 N

(1) (Iso 37 type 2)



The instruction leaflet, the EU Declaration of Conformity and the list of references are available on the website.

PIERCAN  
17-23 rue Marcel Dassault CS 10028 - 93 141 BONDY CEDEX, France  
T : +33 (0)1 45 88 66 27 - F : +33 (0)1 45 80 98 30  
www.piercan.fr - piercan@piercan.fr

