



Dry box glove

# EPDM black/EPDM white

6/10 mm



## SCOPE

Life sciences (pharmaceutical / medical / laboratory industries).  
Nuclear industries.

Black EPDM and White EPDM (Ethylene Propylene Diene Monomer) glove. Halogen and phthalate free. Excellent resistance to chemicals (H<sub>2</sub>O<sub>2</sub>, Peracetic acid, etc.). Very good flexibility and precision. Composition in accordance with the FDA positive list (CFR 21 § 177.2600). High resistance to ozone and UV.

- Economical performance
- Chemical performance
- Dexterity performance
- Mechanical performance
- Storage performance

CE 0333					
			3XX1X	ANP	VIRUS

IN COMPLIANCE WITH 2016/425 EUROPEAN REGULATION (CATEGORY 3 P.P.E.)



## GENERAL INFORMATION

Chemical composition	Two Layer Epdm
Material code	Eb/Ew
Colour	Black And White
Packaging	Individually packed in two-toned black and transparent, heat-sealed and easy-opening pouch. Pack of 10 units.
Care instructions	Store in the original packaging between +5°C and +25°C. Expiry date of 3 years in the original packaging. Wash with soapy water, rinse with clear water and then air-dry at a low temperature (<40°C).
Treatment	Non-recyclable. Disposal as simple non-toxic waste if not contaminated by a hazardous substance.
Sterilisation	Not available in decontaminated or decontaminated-sterile version.
Powdering	Standard: lightly powdered gloves.
Disinfectants	Excellent resistance to the following disinfectants: 0.25% Surfaniols, 0.50% Spetaniols, 10% Sopropyl, 100% Sopropyl, 70% Isopropyl alcohol, Surfa Safe, Actril, 0.50% Henaniols G+R. Good resistance to Klercide CR Biocid B.
Dimensional tolerances	Thickness: 6/10 mm (palm min 4/10, max 7.5/10). Length tolerance (+/- 20 mm). Diameter of the rim: 5 mm (+/-1 mm).

## PHYSICOCHEMICAL PROPERTIES TEMPERATURE RANGE: -30 TO +120°C

Alcohols	---
Acids, bases	---
Strong oxidants	---
Uv, ozone, free radicals, natural ageing	---
Ketone solvents	---
Chlorinated solvents	---
Aromatic solvents	---
Aliphatic oils and solvents	---
Peracetic acid sterilisation (3%)	---
H2O2 Sterilisation (35%)	---
H2O2 Sterilisation (50%)	---
25-50 kGray gamma radiation	---
Autoclave sterilisation (121°C)	---
Protection from ionising radiation	non

\* --- Not recommended --- Can be used under certain conditions --- Acceptable --- Recommended

## MECHANICAL PROPERTIES

100% Modulus <sup>(1)</sup>	Tensile strength <sup>(1)</sup>	Elongation at break <sup>(1)</sup>	Puncture (EN 388)
< 2,5 MPa	> 14 Mpa	> 400%	> 20 N

(1) (Iso 37 type 2)



The instruction leaflet, the EU Declaration of Conformity and the list of references are available on the website.

PIERCAN

17-23 rue Marcel Dassault CS 10028 - 93 141 BONDY CEDEX, France

T : +33 (0)1 45 88 66 27 - F : +33 (0)1 45 80 98 30

www.piercan.fr - piercan@piercan.fr

