

Special mechanical glove or mitt

Natural rubber

15/10 mm



SC-COM-210-Rev 1





| GENERAL INFORMATION | | | |
|------------------------|--|--|--|
| Chemical composition | Polyisoprene | | |
| Material code | н | | |
| Colour | Blond | | |
| Packaging | Individually packed in two-toned black and transparent, heat-seal and easy-opening pouch. Pack of 10 units. | | |
| Care instructions | Store in the original packaging between +5°C and +25°C. Expiry date of 2 years in the original packaging. Wash with soapy water, rinse with clear water and then air-dry at a low temperature (<40°C). | | |
| Treatment | Non-recyclable. Disposal as simple non-toxic waste if not contaminated by a hazardous substance. | | |
| Sterilisation | Not available in decontaminated or decontaminated-sterile version. | | |
| Powdering | Standard: lightly powdered gloves. | | |
| Disinfectants | Glove not suitable for this type of product. | | |
| Dimensional tolerances | Thickness: 15/10 mm (min 12/10, max palm 18/10). Length tolerance (+/- 20 mm). Rim diameter: not applicable. | | |

| PHYSICOCHEMICAL PROPERTIES TEMPERATURE RANGE: -40 TO +80°C | | |
|--|-----|--|
| Alcohols | | |
| Acids, bases | | |
| Strong oxidants | | |
| Uv, ozone, free radicals, natural ageing | | |
| Ketone solvents | | |
| Chlorinated solvents | | |
| Aromatic solvents | | |
| Aliphatic oils and solvents | | |
| Peracétic acid sterilisation (3%) | | |
| H202 Sterilisation (35%) | | |
| H202 Sterilisation (50%) | | |
| 25-50 kGray gamma radiation | | |
| Autoclave sterilisation (121°c) | | |
| Protection from ionising radiation | non | |

 $[^]st$ --- Not recommanded --- Can be used under certain conditions --- Acceptable --- Recommended

| MECHANICAL PROPERTIES | | | | | |
|-----------------------------|---------------------------------|------------------------------------|-------------------|--|--|
| 100% Modulus ⁽¹⁾ | Tensile strength ⁽¹⁾ | Elongation at break ⁽¹⁾ | Puncture (EN 388) | | |
| < 1.5 MPa | > 20 MPa | > 500% | > 20 N | | |

(1) (Iso 37 type 2)



The instruction leaflet, the EU Declaration of Conformity and the list of references are available on the website

PIERCAN

17-23 rue Marcel Dassault CS 10028 - 93 141 BONDY CEDEX, France T:+33 (0)1 45 88 66 27 - F:+33 (0)1 45 80 98 30 www.piercan.fr - piercan@piercan.fr





